

## ZINCOSIL 400

### COLD GALVANIZING ZINC SPRAY

#### CHARACTERISTICS

Components:	Pure zinc 98% in acrylic vehicle (resins)
Pigment Purity:	> 98%
Colour:	light grey
Propellant:	Denatured and odourless hydrocarbon – CFC Free
Dry film Thickness:	20-40 µm micron (cross coating)
Covering Power:	High
Covering value:	About 120ml/m <sup>2</sup> (cross coating)
Dry time:	5-10 minutes. (Fast Drying- It does not drip)
Electric conductivity:	High
Abrasion Resistance:	Very High
Cross cutting:	(DIN 53151-ISO2409) =GT0/GT1
Salt spraying test:	(DIN 50021 – DIN 53167 – ISO 9227) = > 220 hour (salty fog)
Oxidation resistance:	Very Good resistance to corrosion
Processing Temperature:	Spray from +5°C to +35°C (Optimum temperature from +18°C to +25°C)
Temperature resistance:	Layer Coating resistance From -50°C to + 300°C (Metallic powder resists until 700°C)



#### PROPERTIES

- It does not contain chlorinated solvents
- High zinc content
- Fast drying
- It doesn't drip
- High covering power
- It permits over painting
- High resistance to corrosion
- Good resistance to atmospheric agents, washing, oxidation of salty fog
- Colour similar to a hot dip galvanising
- Long lasting protection

#### DESCRIPTION

ZINCOSIL 400 is used for cold galvanization of all metals. Zinc spray with high zinc content is particularly suitable for retouches in soldering, to restore or galvanize metal sheets, to galvanize and protect weather-exposed bolts for long periods, to restore the zinc film on gates, doors, metal sheets, tanks and metal structure.

The Aerosol is endowed with a no-drop nozzle and it permits to use it without staining.

ZINCOSIL 400 is also a good protective against corrosion of atmospheric agents, saltiness, and humidity.

#### INSTRUCTIONS OF USE

Shake the can before use at least for one minute until the little ball inside the can is free to move. During the application shake the product in order to keep it homogeneous. Clean and degrease the parts to treat. Spray at 25 cm distance. After the use overturn the aerosol and spray the product for few seconds to dodge the obstruction of the valve. Shelf life 5 year.

#### PACKAGING

Spray Aerosol ml 400/500

Box 12 Aerosol

Product Code 14510/04 and 14510/05

Revision date 10.12.2017

The information and recommendations contained in this document is offered in good faith based on our current knowledge and belief accurate at the date of publication. Nothing herein is to be considered as a warranty, express or otherwise. In all cases, it is the responsibility of the user to determine the applicability of such information or the suitability of any products for their own particular purpose with local legislation and for obtaining the necessary certifications and authorisations. Siliconi Commerciale's sole warranty is that the products will meet its sales specification. The manufacturer cannot be held responsible in case of damages caused by incorrect use of the product.

® indicates a Registered TradeMarks of Siliconi Commerciale. All Rights Reserved.

SILICONI COMMERCIALE® Technical data- sheet